

Zeta Deck Caulking 1200-FC.

The Zeta Deck Caulking 1200-FC is a one-part moisture curing system. Zeta Deck Caulking 1200-FC has very high resistance to UV, and a high elongation and good adhesion. Zeta Deck caulking 1200-FC can be supplied in three different colors: Black, Gray and White. Zeta Deck Caulking 1200-FC Black is Primer free – Zeta recommend 550 Primer for Zeta Deck Caulking 1200-FC Gray & White.

Application

Apply the Zeta Deck Caulking 1200-FC with a manual or pneumatic gun. Lay the bed careful in the bottom of the seam, let the caulking work itself up the top of the seam, spoon the seam, and leave enough caulking on top for curing.

It is important the seam is sanded, vacuum cleaned and free from dust. Before caulking, clean the seam using a clean cotton cloth with isopropyl or acetone. Run the cloth in the seam to make sure the seam is cleaned correctly.

The Zeta Deck Caulking 1200-FC to cure 3 mm pr day, depends on temperature. Leave the caulking at least 36 to 48 hours before sanding.

If the deck is a re seam and there are doubts if the deck seam is total cleaned and free from old caulking, Zeta recommend using the Zeta 550 primer.

Most wood material can be caulked without primer.

Surface preparation

Surface must be vacuum cleaned, dry, and free from grease. GRP, composite, plywood, metal and aluminum must be primed and sanded with grit 40.

Storage

Keep the Zeta Deck Caulking 1200-FC in a controlled environment, to maximize the shelf life. Temperature between 10 C° and 25 C°.

General Technical Data

Chemical base	Selan	
Density	1,28 g/cm ³	
Color	Black, Grey, White	
Minimum sag and shrink during curing		
Tack free	4 to 6 minutes	
Curing	3 mm pr day	
Elongation of break	350 %	
Shore hardness type a	32	DIN ISO 7619-1
Tear strength	6,5 N/mm	ISO 34-1
Tensile strength	1,45 MPa	DIN 53504
Service temperature	÷40 C and 40 C°	
Cleaning tools, use isopropyl or acetone		

Packing

600 ml sausage, 12 in a box.

300 ml sausage, 12 in a box.

Shelf life 12 months from manufacture date.

Health and safety information

Zeta Marine Group ApS advises to read the SDS and carefully follow the instructions.